



FIRST COPPER TECHNOLOGY CO., LTD. ALLOY GUIDE (1)

Alloy Name	RED & YELLOW BRASS								Tin – Brass	
	C2100	C2200	C2300	C2400	C260S	C2600	C2680	C2801	C4250	
CHEMICAL COMPOSITION (%)	Cu:94.0~96.0 Zn:Bal.	Cu:89.0~91.0 Zn:Bal.	Cu:84.0~86.0 Zn:Bal.	Cu:78.5~81.5 Zn:Bal.	Cu:70.5~73.5 Zn:Bal.	Cu:68.5~71.5 Zn:Bal.	Cu:64.0~68.0 Zn:Bal.	Cu:59.0~62.0 Zn:Bal.	Cu:87~90. Sn:1.5~3.0 Zn:Bal..	
Specific Gravity (gm/cm ³)	8.86	8.80	8.75	8.67	8.53	8.53	8.50	8.39	8.78	
Expansion Coefficient (10 ⁻⁶ /°C)	18.1	18.4	18.7	19.1	19.9	19.9	20.3	20.8	18.5	
Thermal Conductivity (Cal/ cm ² /cm/sec/°C)	0.56	0.45	0.38	0.33	0.29	0.29	0.29	0.29	0.29	
*Electrical Conductivity (Annealing) (%IACS, 20°C)	≥ 56	≥ 44	≥ 37	≥ 32	≥ 28	≥ 28	≥ 27	≥ 28	≥ 26	
Tensile Strength (N/mm ²)	ANNEALED	≥ 205	≥ 225	≥ 245	≥ 255	≥ 295	≥ 295	≥ 295	≥ 320	295~380
	1/4H	250~305	275~335	295~365	295~375	330~415	330~415	330~415	350~440	340~405
	1/2H	270~345	295~365	310~385	320~405	370~440	370~440	370~440	410~490	390~475
	3/4H	--	--	--	--	410~470	410~470	410~470	--	430~510
	H	≥ 280	≥ 320	≥ 340	≥ 375	430~510	430~510	430~510	≥ 450	480~565
	EH	--	--	--	--	510~610	510~610	510~610	--	525~605
	SH	--	--	--	--	565~630	565~630	565~630	--	580~650
	ESH	--	--	--	--	610~725	610~725	610~725	--	≥ 635
Elongation (%)	ANNEALED	≥ 33	≥ 35	≥ 40	≥ 44	≥ 45	≥ 45	≥ 45	≥ 35	≥ 35
	1/4H	≥ 23	≥ 25	≥ 28	≥ 30	≥ 40	≥ 40	≥ 40	≥ 25	≥ 25
	1/2H	≥ 18	≥ 20	≥ 23	≥ 25	≥ 30	≥ 30	≥ 30	≥ 15	≥ 15
	3/4H	--	--	--	--	≥ 20	≥ 20	≥ 20	--	≥ 10
	H	--	--	--	--	≥ 14	≥ 14	≥ 14	--	≥ 5
	EH	--	--	--	--	≥ 8	≥ 8	≥ 8	--	--
	SH	--	--	--	--	≥ 5	≥ 5	≥ 5	--	--
	ESH	--	--	--	--	--	--	--	--	--
Vickers Hardness (Hv)	ANNEALED	≤ 65	≤ 70	≤ 70	≤ 80	≤ 90	≤ 90	≤ 90	--	50~100
	1/4H	65~80	70~95	70~95	75~105	90~105	90~105	90~105	85~105	80~130
	1/2H	80~100	95~120	95~120	100~130	105~130	105~130	105~130	105~130	110~160
	3/4H	--	--	--	--	130~145	130~145	130~145	--	120~170
	H	≥ 100	≥ 120	≥ 120	≥ 125	145~160	145~160	145~160	≥ 130	140~180
	EH	--	--	--	--	160~175	160~175	160~175	--	150~190.
	SH	--	--	--	--	175~190	175~190	175~190	--	165~205
	ESH	--	--	--	--	190~210	190~210	190~210	--	≥ 180
Softening Temp. (°C)	--	--	--	--	--	--	--	--	--	
Modulus of Elasticity (KN/mm ²)	118	118	118	110	110	110	103	103	112	

*Electrical conductivity is the annealing value



FIRST COPPER TECHNOLOGY CO., LTD. ALLOY GUIDE (2)

Alloy Name	HIGH PERFORMANCE ALLOY									
	C1201	C1220	C1221	C151	C19210	C194	C1441	C14415	C1814	
CHEMICAL COMPOSITION (%)	Cu: ≥99.90 P: 0.004~0.015	Cu: ≥99.90 P: 0.015~0.040	Cu: ≥99.90 P: 0.004~0.040	Cu: ≥99.80 Zr:0.05~0.15	Cu: ≥99.6 Fe:0.05~0.15 P:0.025~0.04	Cu: ≥97 Fe:2.1~2.6 P:0.015~0.15 Zn:0.05~0.2	Cu: Bal. Sn:0.10~0.20 P: 0.003~0.024 Fe ≤0.05	Cu+Sn ≥99.96 Sn:0.10~0.15	Cu:Bal. Cr:0.15~0.45 Zr :0.05~0.25 Si:0.005~0.05	
Specific Gravity (gm/cm ³)	8.94	8.94	8.94	8.94	8.94	8.83	8.90	8.92	8.90	
Expansion Coefficient (10 ⁻⁶ /°C)	17.7	17.7	17.7	17.7	17.7	17.6	17.7	17.7	17.1	
Thermal conductivity (Cal/ cm ² /cm/sec/°C)	0.87	0.81	0.81	0.86	0.83	0.625	0.81	0.84	0.755	
*Electrical Conductivity (Annealing) (%IACS, 20°C)	≥95	≥80	≥80	≥90	≥85	≥60	≥80	≥90	≥80	
Tensile Strength (N/mm ²)	ANNEALED	≥195	≥195	≥195	--	255~335	310~380	195~245	195~245	--
	1/4H	215~275	215~275	215~275	245~315	275~355	--	215~295	215~295	--
	1/2H	255~315	255~315	255~315	290~355	295~375	365~435	255~335	255~335	470~550
	3/4H	--	--	--	320~385	--	--	--	--	--
	H	≥290	≥290	≥290	360~435	330~415	410~485	315~395	315~395	510~590
	EH	--	--	--	400~455	≥370	460~505	≥370	385~460	--
	SH	--	--	--	440~490	--	480~525	--	450~510	≥540
Elongation (%)	ANNEALED	≥35	≥35	≥35	--	≥30	≥25	≥35	≥35	--
	1/4H	≥25	≥25	≥25	≥13	≥20	--	≥25	≥25	--
	1/2H	≥15	≥15	≥15	≥6	≥10	≥5	≥15	≥15	≥6
	3/4H	--	--	--	≥5	--	--	--	--	--
	H	≥5	≥5	≥5	≥4	≥5	≥2	≥5	≥5	≥3
	EH	--	--	--	≥3	--	--	≥2	≥2	--
	SH	--	--	--	≥2	--	--	--	--	--
Vickers Hardness (Hv)	ANNEALED	50~65	50~65	50~65	--	≤90	90~110	≤70	≤70	--
	1/4H	60~90	60~90	60~90	--	90~115	--	65~100	65~100	--
	1/2H	85~105	85~105	85~105	100~115	100~125	110~130	80~110	80~110	135~160
	3/4H	--	--	--	105~120	--	--	--	--	--
	H	≥100	≥100	≥100	115~135	110~135	125~145	95~125	100~125	145~170
	EH	--	--	--	120~135	≥115	135~150	≥110	120~145	--
	SH	--	--	--	130~150	--	140~155	--	130~150	≥165
ESH	--	--	--	--	--	≥145	--	≥140	--	
Softening Temp. (°C)	--	--	--	500°C	450°C	1/2H SH 700 390	390°C	--	--	
Modulus of Elasticity (KN/mm ²)	118	118	118	118	118	121	118	128	137	

*Electrical conductivity is the annealing value



FIRST COPPER TECHNOLOGY CO., LTD. ALLOY GUIDE (3)

Alloy Name	HIGH CONDUCTION ALLOY				CORSON		
	OFE (C1010)	OFC (C1020)	ETP (C1100)	C1100P	C7025	C7026	C19010
CHEMICAL COMPOSITION (%)	Cu: ≥99.99 P ≤0.0003 O ₂ ≤0.001 Other ≤0.006	Cu: ≥99.95 O ₂ : ≤ 0.001	Cu: ≥99.90 O ₂ : 0.02~0.045	Cu: ≥99.90 P ≤0.0045	Cu: Bal. Ni:2.2~4.2 Si:0.25~1.20 Mg:0.05~0.30	Cu: Bal. Ni:1.0~3.0 Si:0.20~0.70	Cu: Bal. Ni:0.8~1.8 Si:0.15~0.35 P:0.01~0.05
Specific Gravity (gm/cm ³)	8.94	8.94	8.94	8.94	8.82	8.9	8.9
Expansion Coefficient (10 ⁻⁶ /°C)	17.7	17.0	17.7	17.7	17.3	18.0	16.8
Thermal conductivity (Cal/cm ² /cm/sec/°C)	0.934	0.934	0.935	0.934	0.4	0.37	0.62
*Electrical Conductivity (Annealing) (%IACS, 20°C)	≥101	≥101	≥100	≥99	≥40	≥40	≥55
Tensile Strength (N/mm ²)	ANNEALED	≥195	≥195	≥195	620~755	590~655	--
	1/4H	215~255	215~255	215~255	--	--	360~430
	1/2H	255~315	255~315	255~315	255~315	655~825	675~745
	3/4H	--	--	--	--	685~860	725~795
	H	≥290	≥290	≥290	≥290	795~900	755~835
	EH	--	--	--	--	--	--
	ESH	--	--	--	--	--	--
Elongation (%)	ANNEALED	≥35	≥35	≥35	≥10	≥25	--
	1/4H	≥25	≥25	≥25	--	--	≥12
	1/2H	≥15	≥15	≥15	≥15	≥7	≥10
	3/4H	--	--	--	--	≥5	--
	H	≥5	≥5	≥5	≥5	≥1	≥8
	EH	--	--	--	--	--	≥7
	ESH	--	--	--	--	--	≥6
Vickers Hardness (Hv)	ANNEALED	≤60	≤60	≤60	180~210	170~200	--
	1/4H	60~80	60~80	60~80	60~80	--	100~130
	1/2H	80~100	80~100	80~100	80~100	200~230	190~220
	3/4H	--	--	--	--	220~250	210~240
	H	100~130	100~130	100~130	100~130	240~270	230~260
	EH	--	--	--	--	--	--
	ESH	--	--	--	--	--	--
Softening Temp. (°C)	200°C	--	--	--	--	--	--
Modulus of Elasticity (KN/mm ²)	118	118	118	118	132	130	127

*Electrical conductivity is the annealing value



FIRST COPPER TECHNOLOGY CO., LTD. ALLOY GUIDE (4)

Alloy Name	PHOSPHOR BRONZE								
	C5050	C50710	C50715	C5111	C5102	C5191	C5210	C5240	
CHEMICAL COMPOSITION (%)	Cu: Bal. Sn: 1.0~1.7 P: 0.03~0.35	Cu: Bal. Sn: 1.7~2.3 Ni: 0.1~0.4 P ≤ 0.15	Cu: Bal. Sn: 1.7~2.3 P: 0.025~0.04 Fe: 0.05~0.15	Cu: Bal. Sn: 3.5~4.5 P: 0.03~0.35	Cu: Bal. Sn: 4.5~5.5 P: 0.03~0.35	Cu: Bal. Sn: 5.5~7.0 P: 0.03~0.35	Cu: Bal. Sn: 7.0~9.0 P: 0.03~0.35	Cu: Bal. Sn: 9.0~11.0 P: 0.03~0.35	
Specific Gravity (gm/cm ³)	8.89	8.88	8.9	8.86	8.86	8.83	8.80	8.78	
Expansion Coefficient (10 ⁻⁶ /°C)	17.8	17.0	17.6	17.8	17.8	18	18.2	18.4	
Thermal Conductivity (Cal/ cm ² /cm/sec/°C)	0.49	0.37	0.36	0.20	0.17	0.16	0.15	0.12	
*Electrical Conductivity (Annealing) (%IACS, 20°C)	≥ 40	≥ 32	≥ 35	≥ 20	≥ 20	≥ 13	≥ 12	≥ 10	
Tensile Strength (N/mm ²)	ANNEALED	≥ 245	≥ 315	--	≥ 295	≥ 305	≥ 315	--	--
	1/4H	--	--	--	345~440	375~470	390~510	--	--
	1/2H	360~425	410~510	390~540	410~510	470~570	490~610	470~610	550~650
	3/4H	--	490~590	500~590	--	--	--	--	--
	H	390~470	540~635	540~620	490~590	570~665	590~685	590~705	650~750
	EH	440~510	610~705	≥ 590	≥ 570	≥ 620	≥ 635	685~785	740~830
	SH	≥ 490	--	--	--	--	--	735~835	790~890
Elongation (%)	ANNEALED	≥ 25	≥ 30	--	≥ 38	≥ 40	≥ 42	--	--
	1/4H	--	--	--	≥ 25	≥ 28	≥ 35	--	--
	1/2H	≥ 15	≥ 10	≥ 10	≥ 12	≥ 15	≥ 20	≥ 27	≥ 32
	3/4H	--	--	≥ 7	--	--	--	--	--
	H	≥ 5	≥ 5	≥ 5	≥ 7	≥ 7	≥ 8	≥ 20	≥ 13
	EH	≥ 2	≥ 2	--	≥ 3	≥ 4	≥ 5	≥ 11	≥ 7
	SH	--	--	--	--	--	--	≥ 9	≥ 4
Vickers Hardness (Hv)	ANNEALED	≤ 110	70~115	--	--	--	90~110	--	--
	1/4H	--	--	--	100~130	90~130	110~140	--	--
	1/2H	105~135	125~165	140~170	130~150	130~170	140~180	170~190	190~210
	3/4H	--	150~185	160~185	--	--	--	--	--
	H	125~155	170~205	170~200	150~170	170~190	180~210	190~220	200~230
	EH	135~165	≥ 185	≥ 180	≥ 170	≥ 190	≥ 200	210~230	220~260
	SH	≥ 155	--	--	--	--	--	230~250	250~290
ESH	--	--	--	--	--	--	--	270~300	
Softening Temp.(°C)				--					
Modulus of Elasticity (KN/mm ²)	118	124	120	109	107	109	109	109	

* Electrical conductivity is the annealing value